



ADHESIVES & COATINGS, INC

QURETECH®

TECHNICAL DATA SHEET

Country Club Road, PO Box 628
Grafton, WV 26354
800-847-7773
Fax; 304-265-5202
www.dyna-techadhesives.com
www.quiretech.com

Providing Advanced Water-based and Energy
Curable Coatings and Adhesives
For Over 25 Years
Clean, Safe, Worker Friendly

FlexTac 7465

Remoistenable Envelope Front Gum

FlexTac 7465 is a high solids, high performance product developed as a remoistenable adhesive for use on envelope front gum applications. This adhesive is formulated to be fast setting, non-blocking and has inherent rheological characteristics designed to provide excellent processing on the adhesive coater. FlexTac 7465 exhibits excellent adhesive properties and will not discolor tinted papers. FlexTac 7465 is a higher solids version of FlexTac 272 and also provides improved adhesion to difficult envelope stock.

Additionally, two versions of FlexTac 7465 are available that compensate for climate changes – winter and summer versions. The winter version – which will normally run well fall, winter, and spring – has slightly longer open time to compensate for lower humidity conditions. The summer version has less open time to compensate for higher humidity levels typically encountered during the summer months.

FDA Status

Complies with 21CFR175.105

Applications

Front Gum Adhesive for Envelopes

Typical Properties

Total Solids (1)	71.5 ± 1.0 %
Viscosity ₁ (2)	3250 ± 250 cps
pH	3.0 ± 0.5
Weight per Gallon @ 25°C	10.5 ± 0.2 lbs.
Storage Life	3 months at room temperature
Application Method	Roll coater

Viscosity variations are available for different roller configurations and seasonal weather changes.

FlexTac 7465 was direct coated onto 24# bond paper at 1 wet mil. The adhesive was then allowed to air dry for 24 hours. After drying, the adhesive was then remoistened and laminated to 24# bond paper. The bond was immediately rated as follows:

Immediate Bond:	Deep fiber tear
Layflat of Dried Adhesive Film:	Excellent

(1) Forced air oven 2 hours at 105° C

(2) Brookfield RVT, Spindle #5 @ 20 RPM at 25°C

May 07

This product information is presented in good faith and is to the best of our knowledge, accurate. It is intended to be used as a guide and is not to be construed as a specification for products described herein. Dyna-Tech does not guarantee satisfactory results in any application from reliance upon this information and assumes no liability for any loss or damage arising out of its use. Dyna-Tech recommends that the user of our products thoroughly test them under end use conditions to assure that they meet the requirements of intended applications