



ADHESIVES & COATINGS, INC
QURETECH®
TECHNICAL DATA SHEET

Route 310 North, Country Club Road
PO Box 628, Grafton, WV 26354
304-265-5200, 800-847-7773
Fax; 304-265-5202
www.dyna-techadhesives.com

Providing Advanced Water-based and
Energy Curable Coatings and Adhesives
For Over 25 Years
Clean, Safe, Worker Friendly

DynaCoat EB-1165 (preliminary)

Low Odor, Low Extractable
FDA Compliant for Fiberboard Packaging

**Flexibility To Meet Your Needs
Stability You Can Depend On**

Formulated as an EB curable overprint varnish recommended for fiberboard applications. Provides very fast cure speed, satin gloss, consistent surface mobility and excellent scuff resistance. Substrates varnished with DynaCoat EB-1165 combine %satin look+graphics with durability to provide excellent filling and distribution properties.

Physical Properties (as supplied)

Viscosity, as supplied	200 . 300 cps @ 25°C (RVT #3 @ 20 rpm)
Application viscosity:	As received
Weight per Gallon @ 25°C	9.3 lbs.
Wet color:	White
Color after curing:	Clear, high gloss
Shelf life:	12 months from manufacture date

Suggested Application/Cure Data

Application method:	Flexographic, offset gravure, roll coater and dampener coater
Recommended coating weight:	1.8 . 2.2 lbs. per 3000 square feet
Cure conditions:	2.2 . 2.6 MR
Cleanup:	Use cleaning methods and materials normally used with EB products

Typical Performance Properties

60° Gloss	65+
Slide angle °	20 - 24 (can be custom formulated)
Scuff resistance (100 Sutherland rubs 2# weight)	no ink transfer

May 2010

This product information is presented in good faith and is to the best of our knowledge, accurate. It is intended to be used as a guide and is not to be construed as a specification for products described herein. Dyna-Tech does not guarantee satisfactory results in any application from reliance upon this information and assumes no liability for any loss or damage arising out of its use. Dyna-Tech recommends that the user of our products thoroughly test them under end use conditions to assure that they meet the requirements of intended applications. Statements and methods described herein are based upon the best information and practices known to Dyna-Tech Adhesives, Inc. However, procedures for applications mentioned are suggestions only and are not to be construed as representation or warranties as to performance results. Nor does Dyna-Tech Adhesives, Inc. warrant freedom from patent infringement in the use of any formula or process set forth herein. The user must test performance for acceptability using their conditions.