



ADHESIVES & COATINGS, INC
QURETECH®
TECHNICAL DATA SHEET

Country Club Road, PO Box 628
 Grafton, WV 26354
 800-847-7773
 Fax: 304-265-5202
 www.dyna-techadhesives.com

Providing Advanced Water-based and Energy Curable
 Coatings and Adhesives
 For Over 30 Years.
 Clean, Safe, Worker Friendly

DynaHM 6003

Hot Melt

Flexibility to Meet Your Needs
Stability You Can Depend On

DynaHM 6003 is a low cost, laser friendly hot melt which produces a permanent adhesive film. It has been formulated to provide aggressive quick grab and adhesion to a variety of substrates including PU foam, polyolefin, LDPE, HDPE, PP, PET and corrugated. It may also be used as a laminating adhesive to laminate various substrates including PU foam, polyolefin, LDPE, HDPE, PP, PET and corrugated.

FDA Status Complies with 21CFR175.105

Applications General purpose adhesive

Typical Properties:

| | |
|---------------------------------|--|
| Color: | Amber |
| Type: | Thermoplastic Resin |
| Viscosity @ 325°F | 1500 cps |
| Softening Point: | 300°F |
| Minimum Application Temperature | 30°F |
| Service Temperature Range | 0°F to 180°F |
| Application Temperature: | 325 . 350°F |
| Applicators: | Reservoir pump, Nip roller |
| Cleaning Process: | Cleans up easily with heat and scraper. Purge system with non-reactive oil |
| Packaging: | Steel or fiber drums |
| Machine: | Extruder, reservoir pump |
| Web: | 1 mil Mylar® |
| Coatweight; lb./3000 ft.²: | 15.0 |
| 180° Peel, lbs./in: (1) | 9.0 |
| TLMI Loop Tack, lbs/in²: (2) | 15.3 |
| Shear; 1+x 1+x 1000 gms: (3) | >100 hrs. |

Application Guide:

Apply by any conventional method for high viscosity hot melts including slot die or roll. It is recommended that evaluations of the adhesive be carried out to determine whether the product is suitable for use under individual coater conditions.

Typical adhesive coat weight is 0.8 to 1.2 mils for most applications. Coat the lowest practical temperature, approximately 275°, to avoid thermal degradation. Excessive, or prolonged, heating should be avoided. Enclosure and blanketing of the molten adhesive with nitrogen is suggested.

This product information is presented in good faith and is to the best of our knowledge, accurate. It is intended to be used as a guide and is not to be construed as a specification for products described herein. Dyna-Tech does not guarantee satisfactory results in any application from reliance upon this information and assumes no liability for any loss or damage arising out of its use. Dyna-Tech recommends that the user of our products thoroughly test them under end use conditions to assure that they meet the requirements of intended applications.



ADHESIVES & COATINGS, INC
QURETECH®
TECHNICAL DATA SHEET

Country Club Road, PO Box 628
Grafton, WV 26354
800-847-7773
Fax: 304-265-5202
www.dyna-techadhesives.com

Providing Advanced Water-based and Energy Curable
Coatings and Adhesives
For Over 30 Years.
Clean, Safe, Worker Friendly

Flexibility to Meet Your Needs
Stability You Can Depend On

Storage & Handling:

Under normal conditions, product is stable for 12 months in an unopened container. Store drums in dry areas and keep them tightly covered to prevent contamination. Do not mix with any other products.

Safety Precautions:

Consult Material Safety Data Sheet for hazardous ingredients, disposal methods and related handling information. Use product with adequate ventilation and avoid breathing vapors. Take precautions against skin contact with the molten adhesive to prevent serious burns.

Samples were prepared by direct coating @ 350°F and allowed to cool to 23°C prior to testing

- (1) PSTC-101
- (2) TLMI Loop tack, 1 in². contact area, 12 ipm separation
- (3) PSTC-107

April 2011

This product information is presented in good faith and is to the best of our knowledge, accurate. It is intended to be used as a guide and is not to be construed as a specification for products described herein. Dyna-Tech does not guarantee satisfactory results in any application from reliance upon this information and assumes no liability for any loss or damage arising out of its use. Dyna-Tech recommends that the user of our products thoroughly test them under end use conditions to assure that they meet the requirements of intended applications.